

## TECSUN(UL) PV-Wire

### PHOTOVOLTAIC CABLE

for interconnection wiring of grounded and ungrounded photovoltaic power systems

### Features and Benefits

#### Type Designation

- > TECSUN(UL): Photovoltaic Wire
- > UL Category: ZKLA

#### Conductor

- > Electrolytic tinned copper, Class 5 in accordance with IEC 60228

#### Insulation

- > HEPR complying with UL 1581 Table 50.245
- > Natural color - white

#### Jacket

- > Crosslinked EVA rubber complying with UL 1581 Table 50.245
- > Black color

#### Jacket Printing

- > Typical: PRYSMIAN TECSUN(UL) PV-WIRE E312049 10 AWG / 6mm<sup>2</sup> 600V 90°C Wet 105°C Dry Sun Res -40°C VW-1

#### Nominal Cross Section

- > #16 AWG to 3/0 AWG (1.5mm<sup>2</sup> to 95mm<sup>2</sup>)

#### Performance

- > Meets or exceeds the requirements of UL 4703 and is tested in accordance with relevant UL standards 44, 1581, and 2556; IEC standards 60228, 60754-1, and 60754-2; as well as DIN EN 50305
- > Environmentally Friendly: TECSUN(UL) PV-Wire complies with RoHS directives 2002/95/EG, 2005/69/EG, and 2006/122/EG of the EU
- > 90°C Wet or Dry Operation
- > 105°C Dry Operation

#### Registered Supplier

- > ISO 9001 and ISO 14001
- > UL File E312049

#### Specifications and Ratings

- > UL 4703 Type PV Wire

#### Bend Radius

Static (min) 4 x Cable OD

Dielectric Withstand (AC)	600V	1000V or 2000V
14 - 10 AWG	3.0kV	6.0kV
8 - 2 AWG	3.5kV	7.5kV
1 - 3/0 AWG	4.0kV	9.0kV

#### Temperature Rating

	°C	°F
Ambient	-40 to +90	-40 to +194
Operation (max)	105	221
Short Circuit	250	482

TECSUN (UL) PV-Wire

### Performance Specifications

## TECHNICAL DATA

### Electrical Parameters

- > Rated Voltage (U) 600V AC
- > Test Voltage 6kV (AC) / 10kV (DC) for 5 min
- > Relative Permittivity  $\leq 6$  per UL 2556 Section 6.5.5
- > Long Term Insulation Resistance >  $3G\Omega$  after 12 weeks in water at 90°C, 600V per UL 2556 Section 6.4.4.2.1

### Chemical Parameters

- > Weather Resistance (Sunlight) Meets UL 2556 Section 4.2.8.5; 300 hours  
720 hours per UL 44 Section 5.15.2  
UV-resistance per ISO 4892-2 Method A / UL 1581 Section 1200 (XenoTest)
- > Conductor Corrosion 7 Days at 121°C per UL 2556 Section 8.1
- > Fire Behavior Meets UL 2556 Section 9.1 horizontal flame test  
Vertical flame test per UL 2556 Section 9.5  
VW-1 per UL 1581 Section 1080  
In accordance with IEC 60754-1 for Halogen-Free  
Meets IEC 60754-2 for no corrosivity  
Low Smoke emission per IEC 61034  
In accordance with DIN EN 50305 for no toxicity

### Thermal/Mechanical Parameters

- > Cold Resistance Meets UL 1581 Section 583 at -40°C
- > Insulation Tensile Strength > 1500 lbf/in<sup>2</sup> per UL 1581 Table 50.245

## ORDERING INFORMATION

Nominal Cross-Section	Part No.	Conductor Diameter (inch)	Overall Cable Diameter (inch)	Net Weight (lbs/kft)	Minimum Bend Radius (inch)	Maximum Tensile Load (lbf)	Current Carrying Capacity at 60°C ambient temperature in free air (A)	Short Circuit Current [1s] (A)
16 AWG / 1.5mm <sup>2</sup>	20025133	0.063	0.22	29	1	5	29	190
14 AWG / 2.5mm <sup>2</sup>	20025135	0.075	0.23	36	1	8	41	320
12 AWG / 4.0mm <sup>2</sup>	20025134	0.094	0.25	48	1	13	55	500
10 AWG / 6.0mm <sup>2</sup>	20025136	0.114	0.27	61	2	20	70	760
8 AWG / 10.0mm <sup>2</sup>	20025137	0.157	0.34	101	2	33	98	1260
6 AWG / 16.0mm <sup>2</sup>	20025458	0.217	0.41	150	2	53	132	2010
4 AWG / 25.0mm <sup>2</sup>	20025459	0.252	0.46	212	2	84	176	3150
2 AWG / 35.0mm <sup>2</sup>	20025460	0.295	0.50	278	2	118	218	4410
1 AWG / 50.0mm <sup>2</sup>	20025461	0.354	0.60	398	3	168	276	6300
2/0 AWG / 70.0mm <sup>2</sup>	20025462	0.425	0.67	534	3	236	347	8820
3/0 AWG / 95.0mm <sup>2</sup>	20025463	0.496	0.74	665	3	320	416	12000

Cable diameters and weights are nominal values subject to normal manufacturing variations.

### To place an order, contact us in one of the following ways:

700 Industrial Drive, Lexington SC 29072 - (800) 845-8507 (Inside Sales) - Fax (803) 951-1126 - [energy.cables.na@prysmian.com](mailto:energy.cables.na@prysmian.com)